

WIRE FOR VINEYARD AND AGRICULTURE

SINTERBERG[®]



FEATURES

Technical wire in **plasticized steel** produced by very high technology using the **SINTERBERG**[®] procedure.



TECHNICAL DETAILS

STEEL - UNI EN 16120-2

from C7D

EXTERNAL DIAMETERS RANGE

from 1,40 to 5,00 mm

TENSILE STRENGTH

from 380 to 900 N/mm²

EXTERNAL COATING

Sintered plasticized steel

COATING - UNI EN 10244-2 T1 T2

zinc 99,995% • Class A/B/C/D

zinc 95% + aluminium 5% • Class A/B/C/D

zinc 90% + aluminium 10% • Class A/B/C/D

PACKAGING

RING

| Ø range (mm) | range (kg) |
|--------------|------------|
| 1,40-5,00 | 25-100 |

SPOOLED RING

| Ø range (mm) | range (kg) |
|--------------|------------|
| 1,60-3,50 | 25 |

PRODUCTION RANGE

| Ø (mm) | Development |
|-----------|-------------|
| 1,00-1,40 | 137,20 |
| 1,20-1,60 | 98,40 |
| 1,40-1,80 | 75,50 |
| 1,60-2,00 | 59,10 |
| 1,80-2,20 | 47,00 |
| 2,00-2,50 | 37,20 |
| 2,20-2,70 | 32,30 |
| 2,50-3,00 | 24,50 |
| 2,80-3,30 | 20,10 |
| 3,00-3,50 | 17,50 |
| 3,50-4,00 | 12,80 |
| 4,00-4,50 | 9,90 |
| 4,20-4,70 | 9,00 |
| 4,50-5,00 | 7,70 |