

WIRE FOR VINEYARD AND AGRICULTURE

SINTERBERG[®]



FEATURES

Technical wire in **plasticized steel** produced by very high technology using the **SINTERBERG**[®] procedure.



TECHNICAL DETAILS

STEEL - UNI EN 16120-2

from C7D

EXTERNAL DIAMETERS RANGE

from 1,40 to 5,00 mm

TENSILE STRENGTH

from 380 to 900 N/mm²

EXTERNAL COATING

Sintered plasticized steel

COATING - UNI EN 10244-2 T1 T2

zinc 99,995% • class A/B/C/D

zinc 95% + aluminium 5% • class A/B/C/D

zinc 90% + aluminium 10% • class A/B/C/D

PACKAGING

TIGHT UP COILS

Ø range (mm)	range (kg)
1,40-5,00	40-100

SPOOLED RING

Ø range (mm)	range (kg)
1,60-3,50	25

PRODUCTION RANGE

Ø INTERNAL - Ø EXTERNAL (mm)

DEVELOPMENT (m/kg)

1,00-1,40	137,20
1,20-1,60	98,40
1,40-1,80	75,50
1,60-2,00	59,10
1,80-2,20	47,00
2,00-2,50	37,20
2,20-2,70	32,30
2,50-3,00	24,50
2,80-3,30	20,10
3,00-3,50	17,50
3,50-4,00	12,80
4,00-4,50	9,90
4,20-4,70	9,00
4,50-5,00	7,70